

Product Information

AA23-130

Physical Properties*

DENSITY	22.5 to 24.0 kg/m ³	I.F.D. HARDNESS RANGE (NEWTONS)
TEAR RESISTANCE	400N/m Minimum	IF 40% Minimum 115N
TENSILE STRENGTH	100kPa Minimum	IF 40% Maximum 145N
ELONGATION	200% Minimum	IF 25% RECOVERY 65% Minimum
RESILIENCE	45% Minimum	INDENTATION
COMPRESSION SET (75%)	5% Maximum	(SAG) FACTOR 1.75 Minimum

* When tested internally in accordance with the test methods listed in Australian Standard AS2282.0

Available Colours

Light Grey

Grade Description

General purpose, medium hardness budget grade. Incorporating Ultrafresh™ for antimicrobial protection.

Typical Applications

Seat & back cushions, mattress and armrest overlay.

Information current as at Nov 2016

Contact Dunlop Foams

447 Foleys Rd, Deer Park, VIC 3023

Phone: 1800 736 634 or +617 3345 3644 Fax: 1800 736 994

Email: enquires@dunlopfoams.com.au